

# Comparative Life Cycle Assessment of Polyethylene Terephthalate (PET) and Multilayer Tetra Pak Juice Packaging Systems

Marina Stramarkou<sup>a,b,\*</sup>, Christos Boukouvalas<sup>a</sup>, Panagiota Eleni<sup>a</sup>, Dimitrios Karalekas<sup>c</sup>, Magdalini Krokida<sup>a</sup>

<sup>a</sup> School of Chemical Engineering, National Technical University of Athens, 9 Iroon Polytechniou, Zografou Campus, 15780, Athens, Greece

<sup>b</sup> Institute of Nanoscience and Nanotechnology, National Centre for Scientific Research "Demokritos", Athens, Greece

<sup>c</sup> Department of Industrial Management and Technology, University of Piraeus, A. Dimitriou 80, 18534, Piraeus, Greece  
[m\\_stramarkou@hotmail.com](mailto:m_stramarkou@hotmail.com)

Food packaging provides many vital functions including protection, storage and preservation of products, as well as, information to consumers. However, the overall packaging life cycle generates significant environmental impacts since its production exploits natural resources and energy and causes environmental emissions. Moreover, packaging wastes generate increasing disposal issues, being the second largest fraction of municipal wastes after the organic fraction.

During the last years there is focus on the environmental performance of juice packaging systems. Polyethylene terephthalate (PET) bottles and Tetra Pak multilayer packaging are the dominant juice packaging options. Life cycle assessment (LCA) techniques are used to improve the understanding, as well as, to compare the environmental characteristics of different packaging systems.

This research assesses the environmental impact of the two commonest juice packaging options, including their production along with their final disposal (landfilling, incineration and recycling). The aim is to compare the footprints of PET and Tetra Pak packaging, identify the hot spots and finally discover the most environmentally benign juice packaging. LCA was performed using GABI software, following the ISO 14040 series recommendations, while the impact assessment was carried out using ReCiPe 2016.

The results showed that Tetra Pak was environmentally superior to alternative PET packaging in 12 of the 18 total impact categories. In fact, their differences were significant in climate change and fossil depletion categories, the environmental importance of which is assessed by the Federal Environment Agency as "very high" and "high" respectively. Considering the extended shelf life of juices with Tetra Pak, and the reduced environmental footprint, it can be concluded that there are clear environmental advantages for multilayer Tetra Pak juice packaging over PET bottles.

Keywords: climate change, environmental footprint, end-of-life

## 1. Introduction

The traditional functions of food packaging are to contain and protect food from degradation processes, as well as, to provide information to consumers about the included ingredients and the nutritional value. Packaging provides three main categories of protection: physical protection against mechanical damage during distribution; biological protection against microorganisms, insects or animals and chemical protection against modifications in composition caused by exposure to gases (usually oxygen), moisture or light (Ramos et al., 2015). The beverage sector uses millions of tonnes of packaging per year with juice packaging being the most competitive segment in the global beverage packaging industry. Packaging constitutes a major issue in preserving fruit and vegetable juices. As a result of the emerging consumption of juices, the global juice packaging market has achieved a strong growth and the packaging industry has greatly evolved over the last two decades mainly in terms of packaging materials (Falguera and Ibarz, 2014; Borah and Dutta, 2019).

The use of plastics and especially polyethylene terephthalate (PET) in juice packaging is increased due to the low raw material's cost and its functional advantages, such as the excellent mechanical and optical properties (Falguera and Ibarz, 2014; Ramos *et al.*, 2015). However, plastics' variable permeability to light, gases and low molecular weight molecules (Ramos *et al.*, 2015) along with the poor protection of the quality of oxygen-sensitive beverages over long periods are major concerns for their use in juices (Ros-Chumillas *et al.*, 2007). Nowadays consumers' demand for safer products with higher quality lead the industrial packaging sector to face some remarkable advances (Ramos *et al.*, 2015). One of them is Tetra Pak multilayer packaging, which is produced by laminating six layers of stiff paper (75% of the packaging mass), low density polyethylene (LDPE) (20%) and aluminium foil (Al) (5%). The combination of materials results in the added advantage of properties from each individual material and specifically the rigid shape of paper, the outstanding barrier properties against light, water vapour, oxygen and microorganisms of Al and the layer bonding function of LDPE. Its low weight and cost and the extension of juice shelf life are among the advantages of Tetra Pak multilayer packaging. However, the recycling of Tetra Pak still remains a challenge (Zawadiak, 2017). Nowadays, PET and Tetra Pak packaging systems present the most common options for the packaging of fruit juice products.

The packaging sector produces approximately 2% of the gross national product in developed countries and about half of this packaging is used in food industry. Overall, despite its undeniable usefulness, the life cycle of packaging creates significant environmental impacts. Indeed, its production exploits natural resources and energy and causes environmental emissions (Bertolini *et al.*, 2016). In addition, packaging waste creates disposal issues, making it the second largest fraction of municipal waste after the organic fraction and the percentage is increasing every year (Pasqualino *et al.*, 2011). The contribution of packaging to the overall environmental impact on food supply chains has led to legislation, such as the European Council (1994), but also to a number of studies focusing on packaging management (Tencati *et al.*, 2016; Beitzen-Heineke *et al.*, 2017). The contribution of juices to food packaging fraction is the highest (Pasqualino *et al.*, 2011). It is therefore crucial to assess the environmental impacts of their entire life cycle in order to implement improvements that promote their sustainability. The first step towards improving a process or product is to properly record the current situation in order to evaluate and compare it with any future changes (Boustead, 1993). The comparison of materials and processes to determine the optimum choice presents difficulties.

Life Cycle Analysis (LCA) is a scientific method developed to help address the acute environmental problems of recent years, presenting a wide variety of variations (Guinee, 2002). LCA is the most suitable and valid tool to cover the need for assessment of environmental behavior of products and processes in a reliable way since it is the compilation and evaluation of the inputs, outputs and the potential environmental impacts of a product system throughout its life cycle, as defined by the International Organization for Standardization in the ISO 14040:2006 (ISO, 2006).

The aim of the present study is the assessment of the environmental impact of the two commonest juice packaging options, namely PET and Tetra Pak multilayer packaging systems, including their production along with their final disposal (landfilling, incineration and recycling). The packagings will be compared with each other in terms of their environmental aspects in order to discover the most environmentally benign alternative.

## 2. Materials and Methods

LCA study was performed on GABI ts (v8.7.0.18) software following the ISO 14040 series recommendations (14040:2006 and 14044: 2006). The impact assessment was carried out using ReCiPe 2016 (H) and midpoint impact categories focusing on single environmental problems.

### 2.1 Goal and Scope

The goal of this LCA was to evaluate and compare, in terms of their environmental impacts, two different process chains for the manufacturing and end-of-life of two fruit juice packaging systems: polyethylene terephthalate (PET) bottles and Tetra Pak multilayer packaging. This study's goal was to find the packaging having the lowest environmental impact.

#### 2.1.1 Functional Unit

The functional unit was defined as the packaging containing  $10^{-3} \text{ m}^3$  (one liter) of juice, excluding the cap. PET packaging of  $10^{-3} \text{ m}^3$  of refrigerator juice weighted 48.80 g and Tetra Pak packaging 34.96 g.

#### 2.1.2 System Boundaries

The production and end of life of PET and Tetra Pak packaging systems are the processes that present the greatest changes in the environmental footprint of these packagings. Therefore, processes, such as the filling with juice, the transport and distribution, as well as, the consumption of the products were excluded from the study since they increase the complexity without showing large differences between the two packagings.

## 2.2 Life Cycle Inventory Analysis (LCIA)

After defining the goal and scope of LCA, the next step was the Life Cycle Inventory Analysis (LCIA), which connects all the activities with quantitative data according to the selected functional unit. The data used in this study are derived from laboratory measurements (weight and surface area), publications in scientific papers, Tetra Pak reports and GaBi and Ecoinvent LCA data bases.

Regarding PET bottles, their production included the production of PET granules (raw material), their drying and their extrusion, whereas their end-of-life included recycling at a rate of 30%, incineration at a rate of 40% and landfilling at a rate of 30%. The production of Tetra Pak included the production of raw materials: 4 LDPE layers (20% of total packaging mass), one layer of stiff paper (75%) and one layer of aluminum foil (5%); their bonding and lamination and the final production of the multilayer packaging. Tetra Pak end of life referred to 26% recycling according to latest official global recycling data of Tetra Pak (Tetra Pak, 2020). The remaining 74% was destined to incineration (39%) and landfilling (61%). During recycling, the majority of Tetra Pak units (97 out of 170) recycle only 75% of the packaging (the paper fraction) (Tetra Pak, 2020) and produce paper fibers at a rate of 80% of the paper mass (Xie *et al.*, 2013) used to produce non-packaging paper products, so the same percentages were assumed in the study. From 1 kg of packaging led to recycling, 0.6 kg of paper fibers were produced, while the remaining amount (0.4 kg), which consisted of 0.20 kg of polyethylene, 0.5 kg of aluminum and 0.15 kg of non-recyclable paper, was disposed of for incineration (39%) and landfilling (61%) according to Gabi database. Tetra Pak recycling process is initially carried out in a pulper, data for which were found on the official websites of pulper manufacturers. An average capacity (250 tons per day) was assumed and the energy and water consumptions were found given the final moisture content of the pulper at the end of the process. In total, from 1 kg of Tetra Pak packaging, 0.16 kg was recycled, 0.33 kg was incinerated and 0.51 kg was transported to landfills. Tables 1 and 2 list the input and output data for the main production processes of PET and Tetra Pak packaging systems, respectively.

Table 1. Life cycle inventory with input and output data for the production of PET

Processes	Inputs/ Outputs	Flows	Amounts	Units
Drying	Inputs	Electricity	$1.50 \cdot 10^{-4}$	MJ
		PET	$4.89 \cdot 10^{-2}$	kg
		Thermal Energy	$1.45 \cdot 10^{-2}$	MJ
	Outputs	PET	$4.88 \cdot 10^{-2}$	kg
		Water Vapor	$9.74 \cdot 10^{-5}$	kg
Extrusion	Inputs	Compressed air	$1.17 \cdot 10^{-3}$	Nm <sup>3</sup>
		Electricity	$1.35 \cdot 10^{-1}$	MJ
		Lubricating oil	$6.88 \cdot 10^{-6}$	kg
		PET	$4.88 \cdot 10^{-2}$	kg
	Output	Thermal Energy	$2.09 \cdot 10^{-2}$	MJ
		PET bottle	1.00	pcs

Table 2. Life cycle inventory with input and output data for the production of Tetra Pak packaging

Processes	Inputs/ Outputs	Flows	Amounts	Units
Tetra Pak production	Inputs	Al foil	$1.36 \cdot 10^{-3}$	kg
		LDPE film	$7.95 \cdot 10^{-4}$	kg
		Powder coating	$1.37 \cdot 10^{-4}$	kg
		Corrugated board	$8.03 \cdot 10^{-4}$	kg
		Liquid packaging board (LPB)	$2.13 \cdot 10^{-2}$	kg
	Outputs	Electricity	$2.49 \cdot 10^{-2}$	MJ
		Light fuel oil	$2.26 \cdot 10^{-6}$	kg
		Liquefied petroleum gas (LPG)	$2.69 \cdot 10^{-5}$	kg
		Natural Gas	$2.02 \cdot 10^{-4}$	kg
		Fresh water	$8.83 \cdot 10^{-3}$	kg
Tetra Pak production	Outputs	Tetra Pak packaging	1.00	pcs
		Hazardous waste	$2.57 \cdot 10^{-5}$	kg
		Nitrous oxide	$9.64 \cdot 10^{-9}$	kg
		Volatile organic compounds (VOC)	$7.85 \cdot 10^{-6}$	kg
		Sulphur dioxide	$1.18 \cdot 10^{-8}$	kg
		Non- methane VOC	$4.83 \cdot 10^{-8}$	kg
		Carbon dioxide	$5.30 \cdot 10^{-4}$	kg
		Carbon monoxide	$2.02 \cdot 10^{-7}$	kg
Tetra Pak production	Outputs	Dust (>PM10)	$1.43 \cdot 10^{-9}$	kg
		Methane	$4.85 \cdot 10^{-8}$	kg
		Nitrogen dioxide	$5.34 \cdot 10^{-7}$	kg

## 3. Results and Discussion

The environmental footprint of the production and end-of-life of Tetra Pak and PET juice packaging systems is presented in Figure 1 in detail for the most significant ReCiPe impact category of climate change.

Climate change is solely due to CO<sub>2</sub> emissions and to a lesser extent to methane and N<sub>2</sub>O emissions from combustion of gas for thermal processes and lignite for electricity generation (Huijbregts *et al.*, 2016).

The carbon footprint of Tetra Pak is equal to 0.046 kg CO<sub>2</sub> eq., while the footprint of PET packaging is 2.6 times higher and equal to 0.121 kg CO<sub>2</sub> eq. These results are in line with Tetra Pak reports (Kartonverpackungen, GmbH and GmbH, 2007) and Finkbeiner's study (Finkbeiner *et al.*, 2010).




Figure 1. Production and end-of-life effects of Tetra Pak (TP) and PET juice packaging on climate change impact category (expressed in kg carbon dioxide equivalent - kg CO<sub>2</sub> eq.)

The main factors of Tetra Pak that have the greatest burden in climate change are paper production, aluminum film production and the end-of-life including only landfilling and incineration, whereas regarding PET packaging, the production of PET granules has the greatest share. The converting process plays a minor role. PET granulates have a great share since PET is a fossil based material and has negative impact on the environment. In addition, the weight of PET packaging is higher than that of Tetra Pak and this fact burdens even more the load. In Tetra Pak juice packaging, paper production has a high impact since trees harvested for paper fibers production no longer absorb carbon dioxide and convert it to organic compounds. Concerning aluminum foil, during its production, the largest contributions of greenhouse gases are attributed to the electricity production for electrolysis and thermal energy production for alumina refining (56% and 13% respectively) (Nunez and Jones, 2016). The end-of-life sector related to incineration and landfilling is also considered important in climate change category for both types of packaging due to greenhouse gas emissions during the incineration of packaging materials in municipal solid waste facilities (Markwardt *et al.*, 2017). Tetra Pak recycling footprint is included in the electricity and water consumption sectors. The environmental footprints of the production and end-of-life of PET and Tetra Pak juice packaging systems on the other 17 ReCiPe impact categories are shown in Table 3.

Table 3. Results for midpoint impact categories for production and end-of-life of Tetra Pak and PET packaging

Midpoint Impact category	Tetra Pak	PET	Unit
Fine Particulate Matter Formation	2.75 10 <sup>-5</sup>	3.35 10 <sup>-5</sup>	[kg PM2.5 eq.]
Fossil depletion	0.89 10 <sup>-2</sup>	5.40 10 <sup>-2</sup>	[kg oil eq.]
Freshwater Consumption	2.01 10 <sup>-3</sup>	0.76 10 <sup>-3</sup>	[m <sup>3</sup> ]
Freshwater eco-toxicity	3.66 10 <sup>-5</sup>	3.04 10 <sup>-5</sup>	[kg 1,4 DB eq.]
Freshwater Eutrophication	9.60 10 <sup>-7</sup>	5.98 10 <sup>-7</sup>	[kg P eq.]
Human toxicity, cancer	1.05 10 <sup>-5</sup>	4.17 10 <sup>-5</sup>	[kg 1,4-DB eq.]
Human toxicity, non-cancer	2.00 10 <sup>-3</sup>	7.11 10 <sup>-3</sup>	[kg 1,4-DB eq.]
Ionizing Radiation	1.18 10 <sup>-3</sup>	0.64 10 <sup>-3</sup>	[Bq C-60 eq. to air]
Land use	5.57 10 <sup>-4</sup>	6.38 10 <sup>-4</sup>	[Annual crop eq. ·y]
Marine eco-toxicity	0.58 10 <sup>-4</sup>	1.28 10 <sup>-4</sup>	[kg 1,4-DB eq.]
Marine Eutrophication	1.84 10 <sup>-6</sup>	0.73 10 <sup>-6</sup>	[kg N eq.]
Metal depletion	1.97 10 <sup>-4</sup>	1.97 10 <sup>-4</sup>	[kg Cu eq.]
Photochemical Ozone Formation, Ecosystems	0.50 10 <sup>-1</sup>	1.61 10 <sup>-1</sup>	[kg NO <sub>x</sub> eq.]
Photochemical Ozone Formation, Human Health	3.07 10 <sup>-2</sup>	9.98 10 <sup>-2</sup>	[kg NO <sub>x</sub> eq.]
Stratospheric Ozone Depletion	1.08 10 <sup>-8</sup>	1.48 10 <sup>-8</sup>	[kg CFC-11 eq.]
Terrestrial Acidification	0.92 10 <sup>-4</sup>	1.07 10 <sup>-4</sup>	[kg SO <sub>2</sub> eq.]
Terrestrial eco-toxicity	0.97 10 <sup>-2</sup>	5.06 10 <sup>-2</sup>	[kg 1,4-DB eq.]

In fossil depletion category, the burden of PET packaging is six times higher than Tetra Pak since the former consists exclusively of PET, which is made from fossil fuels, whereas the second consists of 75% paper, which comes from non-fossil sources.

However, the impact of Tetra Pak juice packaging in freshwater consumption is higher than its alternative packaging. This is due to the production and recycling of paper, where huge volumes of water drawn from freshwater sources, such as rivers and lakes, are consumed during the mixing of cellulose fibres with water (paper production) and during the separation of cellulose fibres from foreign materials in the pulper (paper recycling). Except for water consumption, paper significantly contributes to the categories of eutrophication and freshwater eco-toxicity, where Tetra Pak presents a higher load than PET bottle. Paper production

requires chemicals, such as acids/bases for pH control, aluminium sulphate for fibre retention improvement, fillers etc., which end up in freshwater recipients causing chemical contamination. In addition, it contributes organic compounds into surface waters leading to excessive oxygen-consuming reactions and resulting in lack of oxygen in the water (Markwardt *et al.*, 2017). In contrast to freshwater eco-toxicity, in terrestrial and marine eco-toxicity, PET packaging results in a higher environmental load than Tetra Pak. This indicates that the main 1,4- DB emissions of Tetra Pak end up in lakes and freshwater aquifers, while the respective emissions from the production and end-of-life of PET packaging are directed to marine recipients and industrial soil. The elevated 1,4- DB releases of PET bottles are also depicted in the categories of human toxicity (cancer and non-cancer) and are presumably because of the use of antimony, a toxic and potential human carcinogen substance, as catalyst during PET production.

An important share of the high burden of PET packaging in the impact categories of photochemical ozone formation (both for ecosystems and human health) is the end of life. Nitrogen oxides (NO<sub>x</sub>) are emitted as products of the waste incineration mainly through oxidation of nitrogen in the waste (at low temperatures) and less through oxidation of atmospheric nitrogen (at higher temperatures) (Nielsen, 2019). NO<sub>x</sub> emissions contribute to photochemical ozone formation, but are controlled by strict legislation.

On the contrary, incineration and landfilling appear as credits in six impact categories: fine particulate matter formation, fossil depletion, ionizing radiation, land use, stratospheric ozone depletion and terrestrial acidification. Waste incineration leads to the production and recovery of heat and electricity, thus conserving oil and other conventional fossil fuels. This fact has direct benefits to both fossil depletion and ionizing radiation, which refers to anthropogenic emissions of radionuclides into the environment generated during the nuclear fuel cycle, coal burning and extraction of phosphate rocks (Huijbregts *et al.*, 2016). Comparing recycling with incineration and landfilling, the former waste management technique represents a better alternative concerning freshwater consumption, freshwater eco-toxicity, human toxicity, photochemical ozone formation (ecosystems and human health) and terrestrial eco-toxicity categories. A better comparison between the environmental footprints of the two studied juice packaging systems can be performed in Figure 2.




Figure 2. Rates at which the environmental footprint of Tetra Pak is better (blue) and worse (orange) than PET packaging for the eighteen ReCiPe 2016 impact categories (% change over Tetra Pak performance)

Figure 2 shows that Tetra Pak juice packaging demonstrates negative percentages, which indicate inferiority compared to PET packaging, in five categories that concern the aquifer, and more specifically the categories of freshwater and marine eutrophication, freshwater consumption and eco-toxicity. This is due to the production of paper, the main raw material of multilayer packaging, which constitutes 75% of the total packaging mass. On the contrary, PET packaging presents a heavier load in twelve out of eighteen impact categories with the production of PET granules burdening the environmental footprint to a very significant extent. The end-of-life associated with incineration and landfilling of PET bottles has a negative environmental footprint (environmental benefit) in eight categories; while in four categories (metal depletion, terrestrial ecotoxicity and photochemical ozone formation that affects health and ecosystems) is the main contributor in the environmental load due to the emissions produced during combustion.

#### 4. Conclusions

In conclusion, Tetra Pak juice packaging is environmentally superior to PET packaging in twelve of eighteen total impact categories. In fact, the differences between the two packages are significant in the impact

categories of climate change and mineral resources consumption, the environmental significance of which is assessed by the Federal Environment Agency as "very high" and "high" respectively (Kartonverpackungen, Gmbh and Gmbh, 2007). Considering the benefits of Tetra Pak juice packaging in the extended shelf life of the juices, as well as the reduced environmental footprint in most of the impact categories, it can be stated that there are clear environmental advantages for Tetra Pak juice multilayer packaging over PET packaging.

### Acknowledgements

This research is sponsored by Stavros Niarchos Foundation through the Industrial Research Fellowship Program at NCSR "Demokritos" in collaboration with NTUA.

### References

- Beitzen-Heineke E. F., Balta-Ozkan N. and Reefke H., 2017, The prospects of zero-packaging grocery stores to improve the social and environmental impacts of the food supply chain, *Journal of Cleaner Production*, 140, 1528-1541.
- Bertolini M., Bottani E., Vignali G., Volpi A., 2016, Comparative Life Cycle Assessment of Packaging Systems for Extended Shelf Life Milk, *Packaging Technology and Science*, 29, 525-546.
- Borah H., Dutta U., 2019, Trends in Beverage Packaging, Chapter in A. Grumezescu (Ed.), *Trends in Beverage Packaging*, Vol 16, Academic Press, Cambridge, UK, 1-19.
- Boustead, I., 1993, General principles for life cycle assessment databases, *Journal of Cleaner Production*, 1(3-4), 167-172.
- Falguera, V.Ibarz, A., 2014, *Juice processing: Quality, safety and value-added opportunities*, Taylor & Francis Inc, United States.
- Finkbeiner M., Schau E., Lehmann A., Traverso M., 2010, Towards life cycle sustainability assessment, *Sustainability*, 2(10), 3309-3322.
- Guinee, J. B., 2002, Handbook on life cycle assessment operational guide to the ISO standards, *The International Journal of Life Cycle Assessment*, 7, 311.
- Huijbregts, M. A., Steinmann Z., Elshout P., Verones F., Vieira M., Zijp M., Hollander A., Van Zelm R., 2016, ReCiPe 2016: A harmonized life cycle impact assessment method at midpoint and endpoint level *The International Journal of Life Cycle Assessment*, 22, 138-147.
- ISO, 2006, ISO 14040: Environmental Management- Life Cycle Assessment - Principles and Framework, 1-20.
- Elopak GmbH, SIG Combibloc GmbH, Tetra Pak GmbH, 2007, Life cycle assessment Beverage cartons under test, Fachverband Kartonverpackungen für flüssige Nahrungsmittel e.V. (FKN), Wiesbaden, Germany
- Markwardt S., Wellenreuther F., Drescher A., Harth J., Busch, M., 2017, Comparative Life Cycle Assessment of Tetra Pak carton packages and alternative packaging systems for liquid food on the Nordic market, Report commissioned by Tetra Pak International SA, Heidelberg.
- Nielsen O.-K., Nielsen M., Hjelgaard K., Coleman P., Rentz O., Oertel D., Jones H., Wenborn M., Woodfield M., 2019, Municipal waste incineration -Incineration of domestic or municipal wastes (without energy recovery), Chapter in EMEP/EEA air pollutant emission inventory guidebook, European Environmental Agency.
- Nunez P., Jones S., 2016, Cradle to gate: life cycle impact of primary aluminium production, *International Journal of Life Cycle Assessment*, 21, 1594-1604.
- Pasqualino J., Meneses, M., Castells F., 2011, The carbon footprint and energy consumption of beverage packaging selection and disposal, *Journal of Food Engineering*, 103, 357-365.
- Ramos, M., Valdes A., Mellinas A., Carrigos M.C., 2015, New Trends in Beverage Packaging Systems: A Review, *Beverages*. 1(4), 248-272.
- Ros-Chumillas, M. Belissario Y., Iguaz A., Lopez A., 2007, Quality and shelf life of orange juice aseptically packaged in PET bottles, *Journal of Food Engineering*, 79, 234-242.
- Tencati, A., Pogutz B., Moda B., Brambilla M., Cacia C., 2016, Prevention policies addressing packaging and packaging waste: Some emerging trends, *Waste Management*, 56, 35-45.
- Tetra Pak, 2020, Sustainability Report 2020, <<https://www.tetrapak.com/en-gr/sustainability/sustainability-updates>>, accessed 22.03.2021.
- Xie M., Qiao Q., Sun Q., Zhang L., 2013, Life cycle assessment of composite packaging waste management - A Chinese case study on aseptic packaging, *International Journal of Life Cycle Assessment*, 18, 626-635.
- Zawadiak, J., 2017, Tetra Pak Recycling – Current Trends and New Developments, *American Journal of Chemical/Engineering*, 5 (5 3), 37-42.